

材料暨工程實驗室-台中

試驗報告



報告編號： TB-20-07325
C-20-18107

頁數： 1 OF 1

報告日期： 109年12月16日

工程名稱：自測
 承包商：-----
 委託單位：優博企業股份有限公司
 供料廠商：-----
 樣品名稱：SKIN Collection_CARB2_化妝粒片板_18 mm
 加註項目：A
 取樣人員：優博企業股份有限公司-劉邦民
 送驗人員：優博企業股份有限公司-劉邦民
 收件日期：109年12月01日
 試驗日期：109年12月01日~109年12月16日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.下述報告內容標示#處由顧客提供

=====

試驗結果：

試驗項目	試驗結果	方法偵測極限 (MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.2	0.05	CNS 2215(2012)
甲醛釋出量-平均值 (mg/L)	0.2	0.05	

- 註：1.試驗樣品厚度為 18.3 mm
 2.試驗結果低於方法偵測極限值(MDL)之測定值以 "N.D." 表示；
 若高於方法偵測極限值(MDL)，但低於定量極限值(QDL)時，以 "< 0.2" 表示，
 並括號註明其實測值
 3.N.D. = Not Detected / 未檢出
 4.本試驗報告之試驗地點同實驗室地址

----- oOo -----

報告簽署人

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號： TB-20-07949
C-20-19686

頁數： 1 OF 1

報告日期： 109年12月30日

工程名稱： 自測
 承包商： -----
 委託單位： 優博企業股份有限公司
 供料廠商： -----
 樣品名稱： SKIN Collection_CARB2_化妝粒片板_18 mm
 取樣人員： 優博企業股份有限公司-劉邦民
 送驗人員： 優博企業股份有限公司-劉邦民
 收件日期： 109年12月01日
 試驗日期： 109年12月01日~109年12月30日
 備註： 1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.下述報告內容標示#處由顧客提供

試驗結果：

試驗項目	試驗結果	試驗方法
吸水厚度膨脹率 (%)	14	CNS 2215(2017)

註：本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

試驗報告



報告編號：TB-20-07327
C-20-18109

頁數：1 OF 1

報告日期：109年12月30日

工程名稱：自測
 承包商：-----
 委託單位：優博企業股份有限公司
 供料廠商：-----
 樣品名稱：SKIN Collection_CARB2_化妝粒片板_18 mm
 取樣人員：優博企業股份有限公司-劉邦民
 送驗人員：優博企業股份有限公司-劉邦民
 收件日期：109年12月01日
 試驗日期：109年12月01日~109年12月30日
 備註：1.以上資料由顧客提供(收件及試驗日期除外)
 2.除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製
 3.下述報告內容標示#處由顧客提供


試驗結果：

試驗項目	試驗結果	試驗方法
密度 (g/cm ³)	0.77	CNS 2215(2017)
含水率 (%)	8.5	
抗彎強度 (N/mm ²)	24.7	
濕潤抗彎強度-A試驗 (N/mm ²)	12.1	
耐衝擊性 (W ₂ -500, 100 cm)	無龜裂、破壞及剝離的情形 (平均凹陷直徑 9.3 mm)	
木螺釘保持力 (N)	518	
內聚強度 (N/mm ²)	0.8	

註：1.本試驗報告密度、含水率、抗彎強度及耐衝擊性試驗為TAF認證範圍，其餘則非
 2.本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準


 報告簽署人